

Taśmy hartowane

Gatunek	EN	DIN	Grubość [mm]	Szerokość [mm]	Długość [mm]	Rm [Mpa]	HV
1.1204	C55S	CK55	0,01 – 4,0	2,00 – 600	min.300	980-1700	300-520
1.1211	C60S	CK60	0,01 – 4,0	2,00 – 600	min.300	1100-1750	345-530
1.1231	C67S	CK67	0,01 – 4,0	2,00 – 600	min.300	1200-1900	370-580
1.1248	C75S	CK75	0,01 – 4,0	2,00 – 600	min.300	1200-1900	370-580
1.1269	C85S	CK85	0,01 – 4,0	2,00 – 600	min.300	1200-2000	370-605
1.1274	C100S	CK101	0,01 – 4,0	2,00 – 600	min.300	1200-2100	370-630

www.alwoma.pl

